


A32_01_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A32_01_PRECRUSH\A32_01_PRECRUSH178.rdf
 Task file: C:\CamsizerXT\CAMSYS\A32_01_PRECRUSH.afg
 Time: 7/6/2015 , 14:55 , duration 19 min 11 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 72335031 , CCD-Z = 696002
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.8	100.0	0.819	0.890	0.742	26
#20	#16	2.2	99.2	0.823	0.905	0.738	212
#30	#20	2.0	97.0	0.831	0.899	0.735	545
#40	#30	2.2	95.0	0.857	0.898	0.757	1658
#50	#40	2.9	92.8	0.866	0.892	0.760	6796
#60	#50	2.1	89.9	0.875	0.888	0.758	10259
#70	#60	2.9	87.8	0.885	0.887	0.759	24061
#140	#70	40.8	84.9	0.895	0.900	0.745	1530788
PAN	#140	44.1	44.1	0.895	0.922	0.749	127952203



Characteristics

Q3 [%]	x [µm]
10.0	54.5
50.0	114.5
90.0	303.2
SPAN3 =	2.171
U3 =	2.370
Mv3(x) =	172.1 µm
Sigma3(x) =	214.2 µm

Mean value SPHT3 = 0.884
 Mean value Symm3 = 0.907
 Mean value b/l3 = 0.733
 Mean value RDNS_C3 = 0.605
 Mean value SPHT_K3 = 0.669

User