


A32_02_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A32_02_PRECRUSH\A32_02_PRECRUSH183.rdf
 Task file: C:\CamsizerXT\CAMSYS\A32_02_PRECRUSH.afg
 Time: 7/7/2015, 8:42, duration 11 min 16 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 66142672, CCD-Z = 629087
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		2.6	100.0	0.782	0.887	0.758	205
#20	#16	8.3	97.4	0.803	0.888	0.735	1369
#30	#20	8.7	89.1	0.820	0.887	0.735	3914
#40	#30	8.3	80.4	0.846	0.886	0.741	10784
#50	#40	10.5	72.1	0.874	0.889	0.750	40593
#60	#50	10.2	61.6	0.897	0.897	0.754	84565
#70	#60	12.5	51.4	0.908	0.902	0.747	166821
#140	#70	29.6	38.9	0.904	0.905	0.728	1183396
PAN	#140	9.3	9.3	0.890	0.916	0.749	111578199



Characteristics

Q3 [%]	x [μm]
10.0	110.7
50.0	244.9
90.0	878.3
SPAN3 =	3.134
U3 =	2.616
Mv3(x) =	370.1 μm
Sigma3(x) =	305.1 μm

Mean value SPHT3 = 0.871
 Mean value Symm3 = 0.897
 Mean value b/l3 = 0.728
 Mean value RDNS_C3 = 0.438
 Mean value SPHT_K3 = 0.665

User