


A32_03_CRUSH5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A32_03_CRUSH5K\A32_03_CRUSH5K049.rdf
 Task file: C:\CamsizerXT\CAMSYS\A32_03_CRUSH5K.afg
 Time: 8/7/2015, 12:37, duration 34 min 40 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 132684566, CCD-Z = 1263000
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.5	100.0	0.567	0.842	0.704	17
#20	#16	0.2	99.5	0.685	0.857	0.699	41
#30	#20	0.6	99.3	0.722	0.854	0.699	274
#40	#30	1.2	98.7	0.750	0.850	0.710	1759
#50	#40	2.8	97.5	0.790	0.851	0.717	10808
#60	#50	2.7	94.7	0.829	0.859	0.726	22430
#70	#60	6.1	92.0	0.878	0.881	0.748	87505
#140	#70	65.6	85.9	0.900	0.902	0.741	3629159
PAN	#140	20.3	20.3	0.878	0.911	0.725	180258613



Characteristics

Q3 [%]	x [μm]
10.0	72.9
50.0	144.1
90.0	232.6
SPAN3 =	1.108
U3 =	2.174
Mv3(x) =	165.8 μm
Sigma3(x) =	150.9 μm

Mean value SPHT3 = 0.878
 Mean value Symm3 = 0.896
 Mean value b/l3 = 0.721
 Mean value RDNS_C3 = 0.555
 Mean value SPHT_K3 = 0.644

User