


A33_01_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A33_01_6K\A33_01_6K042.rdf
 Task file: C:\CamsizerXT\CAMSYS\A33_01_6K.afg
 Time: 7/30/2015, 11:39, duration 28 min 18 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 51623566, CCD-Z = 798515
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.622	0.780	0.685	7
#50	#40	0.1	100.0	0.743	0.780	0.730	984
#60	#50	2.5	99.9	0.893	0.882	0.776	37158
#70	#60	23.6	97.4	0.930	0.909	0.780	559884
#140	#70	69.8	73.8	0.924	0.912	0.738	3244042
PAN	#140	4.0	4.0	0.859	0.905	0.692	117715459



Characteristics

Q3 [%]	x [μm]
10.0	147.9
50.0	193.9
90.0	230.0
SPAN3 =	0.424
U3 =	1.359
Mv3(x) =	189.4 μm
Sigma3(x) =	39.0 μm

Mean value SPHT3 = 0.916
 Mean value Symm3 = 0.909
 Mean value b/l3 = 0.733
 Mean value RDNS_C3 = 0.618
 Mean value SPHT_K3 = 0.665

User