


A33_01_8K_X2

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A33_01_8K_X2\A33_01_8K_X2047.rdf
 Task file: C:\CamsizerXT\CAMSYS\A33_01_8K_X2.afg
 Time: 7/31/2015 , 10:30 , duration 34 min 18 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 107438918 , CCD-Z = 714676
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.502	0.838	0.645	2
#30	#20	0.0	100.0	0.670	0.891	0.815	3
#40	#30	0.0	100.0	0.769	0.857	0.711	19
#50	#40	0.1	100.0	0.764	0.798	0.731	391
#60	#50	1.6	99.9	0.897	0.886	0.785	19267
#70	#60	19.3	98.3	0.932	0.911	0.787	358305
#140	#70	68.2	79.0	0.922	0.911	0.744	2725048
PAN	#140	10.8	10.8	0.833	0.886	0.667	245935896



Characteristics

Q3 [%]	x [μm]
10.0	99.5
50.0	186.9
90.0	225.6
SPAN3 =	0.675
U3 =	1.962
Mv3(x) =	175.8 μm
Sigma3(x) =	52.3 μm

Mean value SPHT3 = 0.909
 Mean value Symm3 = 0.906
 Mean value b/l3 = 0.732
 Mean value RDNS_C3 = 0.450
 Mean value SPHT_K3 = 0.666

User