


A33_01_8K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A33_01_8K\A33_01_8K048.rdf
 Task file: C:\CamsizerXT\CAMSYS\A33_01_8K.afg
 Time: 8/1/2015 , 13:17 , duration 33 min 54 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 94849278 , CCD-Z = 460325
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.709	0.811	0.703	33
#50	#40	0.4	100.0	0.764	0.811	0.717	1568
#60	#50	2.0	99.6	0.881	0.877	0.768	18901
#70	#60	19.6	97.6	0.929	0.909	0.784	303225
#140	#70	66.3	78.0	0.920	0.910	0.743	2196541
PAN	#140	11.7	11.7	0.829	0.883	0.659	153737662



Characteristics

Q3 [%]	x [μm]
10.0	91.8
50.0	187.6
90.0	227.0
SPAN3 = 0.721	
U3 = 2.135	
Mv3(x) = 175.9 μm	
Sigma3(x) = 53.5 μm	

Mean value SPHT3 = 0.905
 Mean value Symm3 = 0.904
 Mean value b/l3 = 0.728
 Mean value RDNS_C3 = 0.382
 Mean value SPHT_K3 = 0.658

User