


A33_01_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A33_01_PRECRUSH\A33_01_PRECRUSH213.rdf
 Task file: C:\CamsizerXT\CAMSYS\A33_01_PRECRUSH.afg
 Time: 7/8/2015 , 14:32 , duration 11 min 13 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 3069834 , CCD-Z = 67847
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.7	100.0	0.742	0.881	0.779	54
#20	#16	1.8	99.3	0.761	0.882	0.752	346
#30	#20	2.6	97.5	0.772	0.870	0.742	1323
#40	#30	3.2	94.9	0.802	0.860	0.738	4653
#50	#40	9.0	91.7	0.861	0.871	0.748	41153
#60	#50	16.1	82.7	0.902	0.894	0.754	144295
#70	#60	26.3	66.6	0.919	0.905	0.752	379461
#140	#70	39.9	40.3	0.914	0.909	0.718	1110454
PAN	#140	0.4	0.4	0.842	0.906	0.684	10164500



Characteristics

Q3 [%]	x [μm]
10.0	172.3
50.0	224.0
90.0	378.4
SPAN3 = 0.920	
U3 = 1.384	
Mv3(x) = 270.9 μm	
Sigma3(x) = 169.9 μm	

Mean value SPHT3 = 0.891
 Mean value Symm3 = 0.897
 Mean value b/l3 = 0.723
 Mean value RDNS_C3 = 0.443
 Mean value SPHT_K3 = 0.651

User