


A35_02_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A35_02_PRECRUSH\A35_02_PRECRUSH198.rdf
 Task file: C:\CamsizerXT\CAMSYS\A35_02_PRECRUSH.afg
 Time: 7/7/2015, 13:35, duration 9 min 53 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 4648818, CCD-Z = 87099
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.1	100.0	0.590	0.877	0.558	5
#20	#16	0.2	99.9	0.834	0.883	0.729	38
#30	#20	1.1	99.7	0.878	0.898	0.747	546
#40	#30	4.8	98.6	0.893	0.900	0.749	6553
#50	#40	16.7	93.8	0.906	0.902	0.748	62237
#60	#50	14.6	77.1	0.909	0.903	0.738	109413
#70	#60	14.8	62.5	0.914	0.905	0.734	181176
#140	#70	43.2	47.7	0.908	0.909	0.725	1812230
PAN	#140	4.5	4.5	0.880	0.930	0.701	17055605



Characteristics

Q3 [%]	x [μm]
10.0	124.0
50.0	217.4
90.0	378.1
SPAN3 =	1.169
U3 =	1.959
Mv3(x) =	241.0 μm
Sigma3(x) =	118.5 μm

Mean value SPHT3 = 0.899
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.715
 Mean value RDNS_C3 = 0.638
 Mean value SPHT_K3 = 0.621

User