


A35_03_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A35_03_PRECRUSH\A35_03_PRECRUSH203.rdf
 Task file: C:\CamsizerXT\CAMSYS\A35_03_PRECRUSH.afg
 Time: 7/7/2015 , 14:46 , duration 11 min 19 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 18334880 , CCD-Z = 189917
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.3	100.0	0.747	0.852	0.720	20
#20	#16	1.3	99.7	0.803	0.883	0.723	216
#30	#20	2.9	98.4	0.826	0.882	0.721	1324
#40	#30	7.6	95.5	0.868	0.892	0.742	9814
#50	#40	18.5	87.9	0.896	0.900	0.748	67968
#60	#50	13.9	69.4	0.905	0.903	0.741	104077
#70	#60	13.0	55.5	0.910	0.904	0.737	159271
#140	#70	34.5	42.5	0.904	0.906	0.729	1448293
PAN	#140	8.0	8.0	0.884	0.923	0.732	31998741



Characteristics

Q3 [%]	x [μm]
10.0	114.6
50.0	233.2
90.0	456.0
SPAN3 = 1.464	
U3 = 2.310	
Mv3(x) = 270.0 μm	
Sigma3(x) = 169.3 μm	

Mean value SPHT3 = 0.888
 Mean value Symm3 = 0.902
 Mean value b/l3 = 0.720
 Mean value RDNS_C3 = 0.582
 Mean value SPHT_K3 = 0.638

User