


A35_04_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A35_04_PRECRUSH\A35_04_PRECRUSH208.rdf
 Task file: C:\CamsizerXT\CAMSYS\A35_04_PRECRUSH.afg
 Time: 7/8/2015 , 11:29 , duration 10 min 15 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 11553033 , CCD-Z = 114818
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.8	100.0	0.757	0.879	0.706	50
#20	#16	2.3	99.2	0.817	0.887	0.726	343
#30	#20	3.8	96.9	0.834	0.888	0.721	1600
#40	#30	8.1	93.1	0.874	0.895	0.747	10254
#50	#40	19.4	85.0	0.896	0.900	0.747	68602
#60	#50	14.0	65.6	0.902	0.901	0.737	100687
#70	#60	12.9	51.6	0.906	0.902	0.733	151465
#140	#70	32.4	38.7	0.899	0.904	0.724	1291294
PAN	#140	6.3	6.3	0.876	0.922	0.727	19486796



Mean value SPHT3 = 0.884
 Mean value Symm3 = 0.901
 Mean value b/l3 = 0.717
 Mean value RDNS_C3 = 0.560
 Mean value SPHT_K3 = 0.632

User