


A35_05_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A35_05_PRECRUSH\A35_05_PRECRUSH200.rdf
 Task file: C:\CamsizerXT\CAMSYS\A35_05_PRECRUSH.afg
 Time: 7/7/2015, 14:01, duration 11 min 31 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 4124747, CCD-Z = 66322
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.1	100.0	0.821	0.915	0.691	7
#20	#16	0.6	99.9	0.858	0.897	0.742	120
#30	#20	2.5	99.3	0.878	0.899	0.743	1244
#40	#30	7.3	96.8	0.897	0.901	0.750	10705
#50	#40	20.1	89.5	0.904	0.901	0.744	80476
#60	#50	15.4	69.4	0.906	0.902	0.733	124390
#70	#60	14.1	54.0	0.909	0.903	0.727	186426
#140	#70	35.9	39.9	0.901	0.905	0.718	1588281
PAN	#140	4.0	4.0	0.874	0.927	0.702	10691684



Characteristics

Q3 [%]	x [μm]
10.0	129.2
50.0	238.7
90.0	431.6
SPAN3 = 1.267	
U3 = 2.072	
Mv3(x) = 268.2 μm	
Sigma3(x) = 142.5 μm	

Mean value SPHT3 = 0.894
 Mean value Symm3 = 0.903
 Mean value b/l3 = 0.711
 Mean value RDNS_C3 = 0.629
 Mean value SPHT_K3 = 0.614

User