


## A37\_01\_CRUSH5K

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDATA\A37_01_CRUSH5K\A37_01_CRUSH5K063.rdf
Task file:	C:\CamsizerXT\CAMSYS\A37_01_CRUSH5K.afg
Time:	8/4/2015 , 11:45 , duration 19 min 58 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 38516561 , CCD-Z = 422986
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0	0.470	0.781	0.443	1
#20	#16	0.1	100.0	0.730	0.836	0.714	17
#30	#20	0.5	99.9	0.675	0.802	0.695	316
#40	#30	6.6	99.4	0.866	0.878	0.759	12461
#50	#40	38.1	92.8	0.904	0.901	0.750	166302
#60	#50	25.7	54.7	0.909	0.905	0.739	225696
#70	#60	14.7	29.0	0.907	0.906	0.716	202241
#140	#70	10.4	14.3	0.880	0.897	0.680	398542
PAN	#140	3.9	3.9	0.841	0.898	0.675	66726164



Mean value SPHT3 = 0.890
Mean value Symm3 = 0.899
Mean value b/l3 = 0.716
Mean value RDNS_C3 = 0.615
Mean value SPHT_K3 = 0.630

User