


A37_01_CRUSH6K

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\A37_01_CRUSH6K\A37_01_CRUSH6K062.rdf
Task file:	C:\CamsizerXT\CAMSYS\A37_01_CRUSH6K.afg
Time:	8/4/2015 , 10:13 , duration 21 min 33 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 51035217 , CCD-Z = 479045
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.1	100.0	0.594	0.806	0.617	13
#30	#20	0.4	99.9	0.703	0.812	0.707	251
#40	#30	6.2	99.5	0.879	0.885	0.768	12533
#50	#40	37.6	93.3	0.906	0.903	0.751	169679
#60	#50	24.2	55.7	0.910	0.905	0.740	220167
#70	#60	14.3	31.5	0.907	0.905	0.721	204644
#140	#70	12.0	17.2	0.880	0.895	0.686	506750
PAN	#140	5.2	5.2	0.836	0.896	0.668	90544858



Mean value SPHT3 = 0.891
Mean value Symm3 = 0.900
Mean value b/l3 = 0.717
Mean value RDNS_C3 = 0.614
Mean value SPHT_K3 = 0.631

User