


A37\_01\_PRECRUSH

Company:  
 User:  
 Result file: C:\CamsizerXT\CAMDATA\A37\_01\_PRECRUSH\A37\_01\_PRECRUSH315.rdf  
 Task file: C:\CamsizerXT\CAMSYS\A37\_01\_PRECRUSH.afg  
 Time: 7/16/2015, 11:34, duration 8 min 51 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc\_min  
 No. of particles: CCD-B = 5367024, CCD-Z = 67089  
 Velocity adaption: no  
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.4	100.0	0.649	0.857	0.663	31
#20	#16	0.7	99.6	0.688	0.842	0.681	166
#30	#20	2.5	98.9	0.803	0.871	0.720	1450
#40	#30	9.2	96.4	0.882	0.895	0.748	15804
#50	#40	24.3	87.2	0.902	0.901	0.743	110106
#60	#50	16.8	62.9	0.907	0.903	0.734	159387
#70	#60	14.8	46.1	0.911	0.905	0.729	224134
#140	#70	29.4	31.3	0.902	0.906	0.716	1346274
PAN	#140	1.9	1.9	0.867	0.924	0.693	11402793



Mean value SPHT3 = 0.889  
 Mean value Symm3 = 0.901  
 Mean value b/l3 = 0.711  
 Mean value RDNS\_C3 = 0.619  
 Mean value SPHT\_K3 = 0.618

User