


A37_02_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A37_02_PRECRUSH\A37_02_PRECRUSH279.rdf
 Task file: C:\CamsizerXT\CAMSYS\A37_02_PRECRUSH.afg
 Time: 7/14/2015 , 16:28 , duration 9 min 21 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 8709205 , CCD-Z = 79938
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.4	100.0	0.729	0.840	0.687	32
#20	#16	1.2	99.6	0.803	0.876	0.701	239
#30	#20	3.6	98.4	0.871	0.895	0.749	2153
#40	#30	12.0	94.8	0.899	0.903	0.754	19903
#50	#40	25.6	82.8	0.907	0.905	0.745	115052
#60	#50	16.1	57.2	0.910	0.906	0.736	149804
#70	#60	12.9	41.1	0.913	0.907	0.730	193936
#140	#70	24.5	28.2	0.903	0.907	0.721	1167694
PAN	#140	3.7	3.7	0.864	0.918	0.710	15806939



Mean value SPHT3 = 0.895
 Mean value Symm3 = 0.904
 Mean value b/l3 = 0.719
 Mean value RDNS_C3 = 0.632
 Mean value SPHT_K3 = 0.631

User