


A38_01_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A38_01_PRECRUSH\A38_01_PRECRUSH206.rdf
 Task file: C:\CamsizerXT\CAMSYS\A38_01_PRECRUSH.afg
 Time: 7/8/2015 , 10:36 , duration 13 min 6 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 7636114 , CCD-Z = 82020
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.3	100.0	0.842	0.895	0.794	21
#20	#16	1.6	99.7	0.868	0.897	0.748	253
#30	#20	4.0	98.1	0.890	0.905	0.752	1801
#40	#30	10.3	94.1	0.901	0.904	0.754	13077
#50	#40	21.6	83.8	0.906	0.904	0.745	74374
#60	#50	14.5	62.2	0.909	0.904	0.736	103427
#70	#60	12.6	47.7	0.911	0.905	0.730	146812
#140	#70	30.0	35.1	0.903	0.907	0.721	1197072
PAN	#140	5.1	5.1	0.874	0.925	0.714	13754293



Characteristics

Q3 [%]	x [μm]
10.0	127.7
50.0	257.3
90.0	504.1
SPAN3 = 1.463	
U3 = 2.285	
Mv3(x) = 296.9 μm	
Sigma3(x) = 176.6 μm	

Mean value SPHT3 = 0.896
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.718
 Mean value RDNS_C3 = 0.634
 Mean value SPHT_K3 = 0.629

User