


A38\_02\_6K

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDAT\A38_02_6K\A38_02_6K086.rdf
Task file:	C:\CamsizerXT\CAMSYS\A38_02_6K.afg
Time:	7/23/2015 , 10:34 , duration 29 min 9 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 46013778 , CCD-Z = 115983
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0	0.458	0.719	0.580	1
#20	#16	0.0	100.0				0
#30	#20	0.1	100.0	0.666	0.841	0.708	21
#40	#30	0.1	99.9	0.709	0.826	0.701	107
#50	#40	0.9	99.8	0.771	0.825	0.720	2312
#60	#50	2.8	98.9	0.855	0.863	0.745	15097
#70	#60	14.1	96.1	0.909	0.897	0.760	123665
#140	#70	71.9	82.0	0.905	0.903	0.734	1916216
PAN	#140	10.1	10.1	0.828	0.887	0.663	45568174



Mean value SPHT3 = 0.889
Mean value Symm3 = 0.897
Mean value b/l3 = 0.716
Mean value RDNS_C3 = 0.420
Mean value SPHT_K3 = 0.631

User