


A38_03_5K_REDO

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A38_03_5K_REDO\A38_03_5K_REDO050.rdf
 Task file: C:\CamsizerXT\CAMSYS\A38_03_5K_REDO.afg
 Time: 8/1/2015 , 14:42 , duration 29 min 8 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 32535566 , CCD-Z = 149011
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.703	0.820	0.738	53
#50	#40	0.6	100.0	0.752	0.811	0.722	2318
#60	#50	2.7	99.4	0.870	0.869	0.755	22198
#70	#60	13.7	96.7	0.915	0.900	0.761	175454
#140	#70	75.3	83.0	0.907	0.904	0.734	3092952
PAN	#140	7.7	7.7	0.828	0.893	0.645	49763465



Mean value SPHT3 = 0.893
 Mean value Symm3 = 0.899
 Mean value b/l3 = 0.715
 Mean value RDNS_C3 = 0.472
 Mean value SPHT_K3 = 0.627

User