


A38_03_6K_REDO

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A38_03_6K_REDO\A38_03_6K_REDO095.rdf
 Task file: C:\CamsizerXT\CAMSYS\A38_03_6K_REDO.afg
 Time: 8/1/2015 , 12:30 , duration 31 min 30 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 61609308 , CCD-Z = 360467
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.643	0.840	0.620	2
#40	#30	0.1	100.0	0.729	0.833	0.712	154
#50	#40	0.8	99.9	0.776	0.828	0.721	3098
#60	#50	2.8	99.1	0.867	0.870	0.751	21777
#70	#60	13.6	96.3	0.916	0.901	0.763	173421
#140	#70	70.7	82.7	0.910	0.905	0.736	2883326
PAN	#140	12.0	12.0	0.841	0.893	0.667	107156754



Mean value SPHT3 = 0.894
 Mean value Symm3 = 0.900
 Mean value b/l3 = 0.716
 Mean value RDNS_C3 = 0.463
 Mean value SPHT_K3 = 0.630

User