


A38_03_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A38_03_PRECRUSH\A38_03_PRECRUSH211.rdf
 Task file: C:\CamsizerXT\CAMSYS\A38_03_PRECRUSH.afg
 Time: 7/8/2015 , 12:05 , duration 11 min 58 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 3521500 , CCD-Z = 39309
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.1	100.0	0.595	0.840	0.558	3
#20	#16	0.3	99.9	0.873	0.914	0.745	54
#30	#20	1.2	99.6	0.886	0.902	0.761	522
#40	#30	5.4	98.4	0.904	0.904	0.760	6732
#50	#40	17.1	93.0	0.907	0.901	0.752	59382
#60	#50	14.6	75.9	0.909	0.901	0.740	102573
#70	#60	14.3	61.3	0.912	0.902	0.735	160771
#140	#70	42.3	47.0	0.902	0.905	0.723	1671242
PAN	#140	4.7	4.7	0.870	0.925	0.689	6264164



Mean value SPHT3 = 0.897
 Mean value Symm3 = 0.903
 Mean value b/l3 = 0.717
 Mean value RDNS_C3 = 0.654
 Mean value SPHT_K3 = 0.626

User