


A3_02_CRUSH5K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A3_02_CRUSH5K\A3_02_CRUSH5K053.rdf
 Task file: C:\CamsizerXT\CAMSYS\A3_02_CRUSH5K.afg
 Time: 7/1/2015, 10:02, duration 14 min 56 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 29933987, CCD-Z = 340408
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.493	0.645	0.721	12
#40	#30	4.0	100.0	0.871	0.874	0.777	14986
#50	#40	66.7	96.0	0.911	0.906	0.757	549741
#60	#50	20.8	29.3	0.901	0.910	0.698	284682
#70	#60	3.5	8.5	0.883	0.901	0.672	75973
#140	#70	3.3	5.0	0.867	0.890	0.676	269783
PAN	#140	1.7	1.7	0.820	0.897	0.656	61888423



Characteristics

Q3 [%]	x [μm]
10.0	257.8
50.0	326.7
90.0	395.8
SPAN3 = 0.423	
U3 = 1.317	
Mv3(x) = 322.9 μm	
Sigma3(x) = 66.8 μm	

Mean value SPHT3 = 0.898
 Mean value Symm3 = 0.903
 Mean value b/l3 = 0.725
 Mean value RDNS_C3 = 0.634
 Mean value SPHT_K3 = 0.649

User