


A3_03_PRECRUSH

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDATA\A3_03_PRECRUSH\A3_03_PRECRUSH056.rdf
Task file:	C:\CamsizerXT\CAMSYS\A3_03_PRECRUSH.afg
Time:	6/24/2015 , 15:59 , duration 7 min 11 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 1780455 , CCD-Z = 33946
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		3.9	100.0	0.708	0.882	0.742	230
#20	#16	2.6	96.1	0.730	0.855	0.733	696
#30	#20	4.0	93.5	0.754	0.837	0.724	3089
#40	#30	11.6	89.5	0.822	0.848	0.729	25267
#50	#40	60.6	77.9	0.906	0.903	0.747	354499
#60	#50	14.9	17.3	0.896	0.911	0.677	143548
#70	#60	1.6	2.4	0.872	0.905	0.633	24944
#140	#70	0.7	0.8	0.878	0.896	0.679	35913
PAN	#140	0.1	0.1	0.837	0.901	0.663	10991171



Mean value SPHT3 = 0.869
Mean value Symm3 = 0.892
Mean value b/l3 = 0.717
Mean value RDNS_C3 = 0.575
Mean value SPHT_K3 = 0.641

User