


A3_04_CRUSH6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A3_04_CRUSH6K\A3_04_CRUSH6K055.rdf
 Task file: C:\CamsizerXT\CAMSYS\A3_04_CRUSH6K.afg
 Time: 7/1/2015, 14:05, duration 18 min 38 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 30739801, CCD-Z = 349226
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.834	0.889	0.746	6
#40	#30	1.6	100.0	0.856	0.870	0.775	3207
#50	#40	30.0	98.4	0.902	0.899	0.768	144434
#60	#50	34.8	68.4	0.912	0.906	0.752	307837
#70	#60	19.1	33.6	0.906	0.906	0.715	247981
#140	#70	11.5	14.5	0.884	0.898	0.686	404448
PAN	#140	3.0	3.0	0.835	0.898	0.667	51633557



Characteristics

Q3 [%]	x [μm]
10.0	193.5
50.0	272.8
90.0	356.4
SPAN3 =	0.597
U3 =	1.482
Mv3(x) =	271.5 μm
Sigma3(x) =	71.5 μm

Mean value SPHT3 = 0.896
 Mean value Symm3 = 0.901
 Mean value b/l3 = 0.726
 Mean value RDNS_C3 = 0.579
 Mean value SPHT_K3 = 0.657

User