


A3_04_PRECRUSH

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDATA\A3_04_PRECRUSH\A3_04_PRECRUSH205.rdf
Task file:	C:\CamsizerXT\CAMSYS\A3_04_PRECRUSH.afg
Time:	6/29/2015 , 15:48 , duration 8 min 22 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 1775015 , CCD-Z = 25803
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		3.1	100.0	0.698	0.869	0.740	151
#20	#16	2.1	96.9	0.728	0.858	0.733	418
#30	#20	3.9	94.8	0.762	0.853	0.734	2419
#40	#30	11.3	90.9	0.804	0.854	0.728	17723
#50	#40	22.4	79.6	0.875	0.883	0.741	104121
#60	#50	23.8	57.2	0.908	0.903	0.744	223689
#70	#60	21.0	33.4	0.914	0.909	0.726	304798
#140	#70	12.4	12.4	0.899	0.908	0.680	298308
PAN	#140	0.0	0.0	0.842	0.890	0.639	4105366



Mean value SPHT3 = 0.867
Mean value Symm3 = 0.889
Mean value b/l3 = 0.714
Mean value RDNS_C3 = 0.456
Mean value SPHT_K3 = 0.638

User