


A3-3_crush6k

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A3-3_crush6k\A3-3_crush6k011.rdf
 Task file: C:\CamsizerXT\CAMSYS\A3-3_crush6k.afg
 Time: 11/12/2014, 14:41, duration 18 min 40 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 88945643, CCD-Z = 794690
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.930	0.889	0.864	1
#30	#20	0.0	100.0	0.699	0.799	0.735	8
#40	#30	1.8	100.0	0.876	0.876	0.793	8731
#50	#40	59.7	98.2	0.915	0.908	0.767	651187
#60	#50	22.1	38.5	0.901	0.908	0.708	396373
#70	#60	5.3	16.4	0.889	0.899	0.697	161321
#140	#70	7.1	11.1	0.870	0.890	0.682	755918
PAN	#140	4.0	4.0	0.835	0.897	0.660	212070903



Characteristics

Q3 [%]	x [μm]
10.0	199.9
50.0	315.4
90.0	379.4
SPAN3 =	0.569
U3 =	1.640
Mv3(x) =	301.5 μm
Sigma3(x) =	78.4 μm

Mean value SPHT3 = 0.898
 Mean value Symm3 = 0.904
 Mean value b/l3 = 0.728
 Mean value RDNS_C3 = 0.632
 Mean value SPHT_K3 = 0.657

User