


A41_02_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A41_02_PRECRUSH\A41_02_PRECRUSH182.rdf
 Task file: C:\CamsizerXT\CAMSYS\A41_02_PRECRUSH.afg
 Time: 7/6/2015, 15:56, duration 9 min 52 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 6062321, CCD-Z = 54436
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.8	100.0	0.716	0.847	0.707	71
#20	#16	2.5	99.2	0.723	0.849	0.697	551
#30	#20	4.1	96.7	0.768	0.859	0.700	2342
#40	#30	6.5	92.6	0.823	0.868	0.723	11382
#50	#40	22.9	86.1	0.885	0.892	0.746	119849
#60	#50	22.1	63.2	0.901	0.901	0.734	222799
#70	#60	17.4	41.1	0.904	0.904	0.720	274178
#140	#70	22.0	23.7	0.896	0.905	0.708	953124
PAN	#140	1.7	1.7	0.862	0.920	0.711	8629902



Characteristics

Q3 [%]	x [μm]
10.0	169.4
50.0	268.6
90.0	506.1
SPAN3 =	1.253
U3 =	1.722
Mv3(x) =	316.1 μm
Sigma3(x) =	189.7 μm

Mean value SPHT3 = 0.872
 Mean value Symm3 = 0.894
 Mean value b/l3 = 0.708
 Mean value RDNS_C3 = 0.490
 Mean value SPHT_K3 = 0.617

User