


A41_03_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A41_03_PRECRUSH\A41_03_PRECRUSH194.rdf
 Task file: C:\CamsizerXT\CAMSYS\A41_03_PRECRUSH.afg
 Time: 7/7/2015 , 11:23 , duration 8 min 59 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 9542683 , CCD-Z = 94793
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.5	100.0	0.745	0.865	0.716	44
#20	#16	2.0	99.5	0.761	0.864	0.706	464
#30	#20	5.3	97.5	0.825	0.878	0.722	3295
#40	#30	13.5	92.2	0.866	0.890	0.733	23538
#50	#40	28.1	78.7	0.887	0.897	0.734	133797
#60	#50	17.3	50.6	0.896	0.901	0.727	168873
#70	#60	12.5	33.3	0.899	0.902	0.719	199789
#140	#70	18.0	20.8	0.888	0.901	0.708	839713
PAN	#140	2.8	2.8	0.860	0.915	0.720	17847283



Mean value SPHT3 = 0.872
 Mean value Symm3 = 0.895
 Mean value b/l3 = 0.706
 Mean value RDNS_C3 = 0.508
 Mean value SPHT_K3 = 0.612

User