


A42_01_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A42_01_PRECRUSH\A42_01_PRECRUSH209.rdf
 Task file: C:\CamsizerXT\CAMSYS\A42_01_PRECRUSH.afg
 Time: 7/8/2015 , 11:41 , duration 10 min 20 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 19219552 , CCD-Z = 132488
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.7	100.0	0.722	0.855	0.691	56
#20	#16	2.2	99.3	0.748	0.868	0.675	414
#30	#20	3.8	97.1	0.791	0.867	0.704	2105
#40	#30	10.5	93.3	0.855	0.883	0.739	17983
#50	#40	31.8	82.8	0.889	0.898	0.739	144790
#60	#50	18.6	51.0	0.896	0.902	0.723	166647
#70	#60	11.6	32.4	0.897	0.903	0.713	168005
#140	#70	16.5	20.8	0.890	0.902	0.708	754098
PAN	#140	4.3	4.3	0.866	0.914	0.724	27639925



Mean value SPHT3 = 0.871
 Mean value Symm3 = 0.895
 Mean value b/l3 = 0.707
 Mean value RDNS_C3 = 0.519
 Mean value SPHT_K3 = 0.613

User