


A46_01_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A46_01_PRECRUSH\A46_01_PRECRUSH273.rdf
 Task file: C:\CamsizerXT\CAMSYS\A46_01_PRECRUSH.afg
 Time: 7/14/2015, 15:03, duration 9 min 0 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 4984749, CCD-Z = 51851
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.3	100.0	0.717	0.863	0.714	28
#20	#16	0.7	99.7	0.726	0.844	0.645	135
#30	#20	1.6	99.0	0.776	0.864	0.680	860
#40	#30	4.7	97.4	0.865	0.886	0.740	8296
#50	#40	22.8	92.7	0.898	0.898	0.749	113105
#60	#50	21.7	69.9	0.907	0.904	0.735	201685
#70	#60	17.9	48.2	0.911	0.907	0.725	274582
#140	#70	28.8	30.3	0.902	0.908	0.715	1276762
PAN	#140	1.5	1.5	0.849	0.922	0.676	9024070



Mean value SPHT3 = 0.890
 Mean value Symm3 = 0.901
 Mean value b/l3 = 0.711
 Mean value RDNS_C3 = 0.554
 Mean value SPHT_K3 = 0.616

User