


A47_01_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A47_01_PRECRUSH\A47_01_PRECRUSH180.rdf
 Task file: C:\CamsizerXT\CAMSYS\A47_01_PRECRUSH.afg
 Time: 7/6/2015 , 15:31 , duration 14 min 10 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 9186083 , CCD-Z = 94910
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0	0.686	0.885	0.792	3
#20	#16	0.3	100.0	0.790	0.912	0.812	36
#30	#20	0.5	99.7	0.750	0.878	0.727	206
#40	#30	1.7	99.2	0.772	0.871	0.722	1701
#50	#40	1.8	97.5	0.793	0.861	0.714	4802
#60	#50	1.3	95.7	0.819	0.853	0.728	8498
#70	#60	3.4	94.4	0.857	0.865	0.743	35825
#140	#70	74.3	91.0	0.885	0.897	0.726	3287251
PAN	#140	16.7	16.7	0.868	0.923	0.696	14170881



Characteristics

Q3 [%]	x [μm]
10.0	95.7
50.0	137.1
90.0	206.6
SPAN3 = 0.808	
U3 = 1.542	
Mv3(x) = 156.0 μm	
Sigma3(x) = 92.5 μm	

Mean value SPHT3 = 0.868
 Mean value Symm3 = 0.897
 Mean value b/l3 = 0.703
 Mean value RDNS_C3 = 0.558
 Mean value SPHT_K3 = 0.600

User