


A6_01_PRECRUSH

Company:	
User:	
Result file:	C:\CamsizerXT\CAMDATA\A6_01_PRECRUSH\A6_01_PRECRUSH275.rdf
Task file:	C:\CamsizerXT\CAMSYS\A6_01_PRECRUSH.afg
Time:	7/14/2015 , 15:29 , duration 11 min 48 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm
Particle model:	xc_min
No. of particles:	CCD-B = 9681693 , CCD-Z = 159358
Velocity adaption:	no
Fitting:	no
Material:	

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		5.0	100.0	0.782	0.896	0.742	133
#20	#16	2.5	95.0	0.781	0.881	0.733	462
#30	#20	4.2	92.5	0.792	0.878	0.742	2352
#40	#30	9.1	88.3	0.816	0.878	0.751	14292
#50	#40	18.7	79.2	0.837	0.880	0.750	81713
#60	#50	13.4	60.5	0.851	0.882	0.747	121654
#70	#60	12.5	47.1	0.863	0.883	0.746	188225
#140	#70	25.2	34.6	0.867	0.882	0.732	1200502
PAN	#140	9.4	9.4	0.878	0.919	0.733	25160350



Mean value SPHT3 = 0.842
Mean value Symm3 = 0.884
Mean value b/l3 = 0.731
Mean value RDNS_C3 = 0.403
Mean value SPHT_K3 = 0.688

User