


A7-3-Crush 5k

Company: Retsch Technology
 User:
 Result file: C:\CAMSIZER-XT-6-0-0-1005\CamsizerXT\CAMDAT\A7-3-Crush 5k\A7-3-Crush 5k_2014-06-10_020.rdf
 Task file: C:\CAMSIZER-XT-6-0-0-1005\CamsizerXT\CAMSYS\A7-3-Crush 5k.afg
 Time: 06/10/14 , 13:17 , duration 25 min 13 s at 0.4 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 38529420 , CCD-Z = 513054
 Velocity adaption: X-Fall-Sand-1micron-3mm.ftv
 Fitting: no

Material:

ASTM(+)	No(-)	p3 [%]
> #16		0.00
#20	#16	0.00
#30	#20	0.00
#40	#30	0.00
#50	#40	0.03
#60	#50	1.56
#70	#60	13.47
#140	#70	75.33
PAN	#140	9.61



Characteristics

Q3 [%]	x [μm]
10.0	107.08
50.0	169.36
90.0	220.82
Mv3(x) =	165.43 μm
Sigma3(x) =	45.51 μm

User