


A7-3-Crush 6k

Company: Retsch Technology
 User:
 Result file: C:\CAMSizer-XT-6-0-0-1005\CamsizerXT\CAMDAT\A7-3-Crush 6k\A7-3-Crush 6k_2014-06-10_018.rdf
 Task file: C:\CAMSizer-XT-6-0-0-1005\CamsizerXT\CAMSYS\A7-3-Crush 6k.afg
 Time: 06/10/14 , 11:29 , duration 27 min 18 s at 0.4 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 52349250 , CCD-Z = 666647
 Velocity adaption: X-Fall-Sand-1micron-3mm.ftv
 Fitting: no

Material:

ASTM(+)	No(-)	p3 [%]
> #16		0.00
#20	#16	0.00
#30	#20	0.00
#40	#30	0.00
#50	#40	0.03
#60	#50	1.28
#70	#60	11.98
#140	#70	74.64
PAN	#140	12.07



Characteristics

Q3 [%]	x [μm]
10.0	100.11
50.0	164.29
90.0	218.14
Mv3(x) =	160.40 μm
Sigma3(x) =	47.23 μm

User