


A7_01_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDATA\A7_01_PRECRUSH\A7_01_PRECRUSH142.rdf
 Task file: C:\CamsizerXT\CAMSYS\A7_01_PRECRUSH.afg
 Time: 6/16/2015, 9:19, duration 11 min 15 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 47892263, CCD-Z = 334702
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		19.1	100.0	0.775	0.892	0.721	788
#20	#16	7.7	80.9	0.778	0.882	0.704	1478
#30	#20	7.0	73.2	0.791	0.878	0.717	3891
#40	#30	6.4	66.2	0.809	0.872	0.723	10039
#50	#40	8.1	59.8	0.843	0.872	0.735	38953
#60	#50	8.8	51.7	0.890	0.889	0.753	92563
#70	#60	11.8	42.9	0.911	0.901	0.749	195623
#140	#70	28.1	31.1	0.909	0.906	0.729	1348275
PAN	#140	3.0	3.0	0.869	0.905	0.712	75495596



Characteristics

Q3 [%]	x [μm]
10.0	146.8
50.0	286.2
90.0	1778.2
SPAN3 = 5.701	
U3 = 2.923	
Mv3(x) = 661.8 μm	
Sigma3(x) = 718.1 μm	

Mean value SPHT3 = 0.846
 Mean value Symm3 = 0.892
 Mean value b/l3 = 0.717
 Mean value RDNS_C3 = 0.339
 Mean value SPHT_K3 = 0.644

User