


A7_02_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A7_02_SV_14_PRECRUSH\A7_02_SV_14_PRECRUSH175.rdf
 Task file: C:\CamsizerXT\CAMSYS\A7_02_SV_14_PRECRUSH.afg
 Time: 6/16/2015 , 15:35 , duration 13 min 6 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 17307607 , CCD-Z = 257547
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		12.1	100.0	0.811	0.904	0.766	546
#20	#16	7.8	87.9	0.808	0.897	0.739	961
#30	#20	6.0	80.1	0.805	0.890	0.735	2097
#40	#30	6.2	74.1	0.828	0.887	0.757	6603
#50	#40	9.6	67.9	0.859	0.887	0.759	30021
#60	#50	7.5	58.3	0.881	0.891	0.756	47743
#70	#60	6.6	50.8	0.894	0.895	0.746	68749
#140	#70	23.6	44.2	0.900	0.900	0.743	1178769
PAN	#140	20.6	20.6	0.896	0.926	0.736	39474066



Characteristics

Q3 [%]	x [μm]
10.0	85.7
50.0	245.5
90.0	1267.4
SPAN3 = 4.813	
U3 = 3.683	
Mv3(x) = 451.0 μm	
Sigma3(x) = 460.2 μm	

Mean value SPHT3 = 0.862
 Mean value Symm3 = 0.902
 Mean value b/l3 = 0.736
 Mean value RDNS_C3 = 0.493
 Mean value SPHT_K3 = 0.682

User