


A7_02_SV_14_SHERE_AND_ROUND

Company:
 User:
 Result file: C:\...T\CAMDATA\A7_02_SV_14_SHERE_AND_ROUND\A7_02_SV_14_SHERE_AND_ROUND168.rdf
 Task file: C:\CamsizerXT\CAMSYS\A7_02_SV_14_SHERE_AND_ROUND.afg
 Time: 6/16/2015, 14:12, duration 12 min 22 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 3811637, CCD-Z = 99007
 Velocity adaption: no
 Fitting: no

Material:

| ASTM(+) | No(-) | retained [%] | passing [%] | SPHT3 | Symm3 | b/l3 | PDN |
|---------|-------|--------------|-------------|-------|-------|-------|----------|
| > #16 | | 0.0 | 100.0 | | | | 0 |
| #20 | #16 | 0.0 | 100.0 | | | | 0 |
| #30 | #20 | 0.0 | 100.0 | | | | 0 |
| #40 | #30 | 0.0 | 100.0 | | | | 0 |
| #50 | #40 | 0.0 | 100.0 | 0.595 | 0.720 | 0.708 | 30 |
| #60 | #50 | 0.9 | 100.0 | 0.863 | 0.867 | 0.775 | 3123 |
| #70 | #60 | 9.7 | 99.1 | 0.901 | 0.892 | 0.772 | 54329 |
| #140 | #70 | 77.4 | 89.4 | 0.899 | 0.902 | 0.744 | 1661509 |
| PAN | #140 | 12.0 | 12.0 | 0.886 | 0.927 | 0.703 | 14762397 |



Mean value SPHT3 = 0.891
 Mean value Symm3 = 0.902
 Mean value b/l3 = 0.727
 Mean value RDNS_C3 = 0.662
 Mean value SPHT_K3 = 0.656

User