


A7_04_SV_14_5K_SECONDRUN

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A7_04_SV_14_5K_SECONDRUN\A7_04_SV_14_5K_SECONDRUN048.rdf
 Task file: C:\CamsizerXT\CAMSYS\A7_04_SV_14_5K_SECONDRUN.afg
 Time: 6/19/2015 , 12:58 , duration 25 min 58 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 69390716 , CCD-Z = 605910
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.815	0.872	0.762	1
#40	#30	0.0	100.0	0.791	0.883	0.671	5
#50	#40	0.0	100.0	0.725	0.793	0.749	184
#60	#50	0.3	100.0	0.822	0.838	0.762	3839
#70	#60	3.0	99.7	0.894	0.884	0.777	59823
#140	#70	85.0	96.7	0.909	0.906	0.752	6423131
PAN	#140	11.7	11.7	0.865	0.910	0.696	119632779



Characteristics

Q3 [%]	x [μm]
10.0	102.4
50.0	144.7
90.0	190.5
SPAN3 =	0.608
U3 =	1.506
Mv3(x) =	145.1 μm
Sigma3(x) =	37.4 μm

Mean value SPHT3 = 0.898
 Mean value Symm3 = 0.904
 Mean value b/l3 = 0.731
 Mean value RDNS_C3 = 0.593
 Mean value SPHT_K3 = 0.664

User