


A7_04_SV_14_6K

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A7_04_SV_14_6K\A7_04_SV_14_6K177.rdf
 Task file: C:\CamsizerXT\CAMSYS\A7_04_SV_14_6K.afg
 Time: 6/16/2015, 15:55, duration 28 min 52 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 80743541, CCD-Z = 810454
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.947	0.937	0.824	2
#50	#40	0.0	100.0	0.717	0.786	0.736	175
#60	#50	0.3	100.0	0.823	0.842	0.762	3827
#70	#60	3.3	99.7	0.896	0.886	0.779	64334
#140	#70	83.5	96.4	0.911	0.908	0.754	5925522
PAN	#140	12.9	12.9	0.885	0.919	0.721	116906863



Characteristics

Q3 [%]	x [μm]
10.0	99.3
50.0	146.1
90.0	192.5
SPAN3 = 0.638	
U3 = 1.570	
Mv3(x) = 145.4 μm	
Sigma3(x) = 39.1 μm	

Mean value SPHT3 = 0.901
 Mean value Symm3 = 0.906
 Mean value b/l3 = 0.736
 Mean value RDNS_C3 = 0.640
 Mean value SPHT_K3 = 0.674

User