


A7-1_Crush7k

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\A7-1_Crush7k\A7-1_Crush7k141.rdf
 Task file: C:\CamsizerXT\CAMSYS\A7-1_Crush7k.afg
 Time: 6/16/2015, 8:45, duration 30 min 0 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 147788437, CCD-Z = 1283495
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0	0.599	0.727	0.591	4
#40	#30	0.0	100.0	0.511	0.700	0.637	2
#50	#40	0.1	100.0	0.731	0.779	0.736	333
#60	#50	1.1	99.9	0.884	0.878	0.780	15040
#70	#60	11.0	98.8	0.923	0.905	0.781	221741
#140	#70	75.5	87.8	0.917	0.909	0.748	4564077
PAN	#140	12.3	12.3	0.863	0.901	0.700	228128026



Characteristics

Q3 [%]	x [μm]
10.0	95.4
50.0	163.3
90.0	216.2
SPAN3 = 0.739	
U3 = 1.831	
Mv3(x) = 158.5 μm	
Sigma3(x) = 49.4 μm	

Mean value SPHT3 = 0.905
 Mean value Symm3 = 0.906
 Mean value b/l3 = 0.732
 Mean value RDNS_C3 = 0.590
 Mean value SPHT_K3 = 0.665

User