


B35_02_SV_14_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B35_02_SV_14_PRECRUSH\B35_02_SV_14_PRECRUSH186.rdf
 Task file: C:\CamsizerXT\CAMSYS\B35_02_SV_14_PRECRUSH.afg
 Time: 7/7/2015, 9:19, duration 15 min 41 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 28177883, CCD-Z = 438315
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.6	100.0	0.748	0.878	0.745	22
#20	#16	2.4	99.4	0.755	0.887	0.730	234
#30	#20	3.3	97.0	0.783	0.884	0.738	846
#40	#30	4.5	93.7	0.797	0.876	0.740	3423
#50	#40	6.2	89.2	0.822	0.874	0.742	13206
#60	#50	3.6	83.0	0.836	0.870	0.736	16421
#70	#60	3.4	79.4	0.847	0.869	0.734	25137
#140	#70	44.1	76.0	0.886	0.893	0.737	1878670
PAN	#140	31.9	31.9	0.888	0.923	0.712	74564655



Characteristics

Q3 [%]	x [μm]
10.0	80.8
50.0	123.1
90.0	447.8
SPAN3 = 2.982	
U3 = 1.684	
Mv3(x) = 205.6 μm	
Sigma3(x) = 217.0 μm	

Mean value SPHT3 = 0.862
 Mean value Symm3 = 0.897
 Mean value b/l3 = 0.713
 Mean value RDNS_C3 = 0.527
 Mean value SPHT_K3 = 0.628

User