


B51_01_5KCRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B51_01_5KCRUSH\B51_01_5KCRUSH108.rdf
 Task file: C:\CamsizerXT\CAMSYS\B51_01_5KCRUSH.afg
 Time: 10/12/2015 , 15:50 , duration 34 min 14 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 99211742 , CCD-Z = 1306241
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.487	0.848	0.725	2
#30	#20	0.1	100.0	0.656	0.839	0.726	18
#40	#30	0.2	99.9	0.726	0.835	0.715	333
#50	#40	1.0	99.7	0.772	0.833	0.720	3853
#60	#50	2.0	98.7	0.843	0.859	0.742	16151
#70	#60	9.6	96.7	0.899	0.890	0.764	126194
#140	#70	74.3	87.1	0.907	0.903	0.736	2931016
PAN	#140	12.8	12.8	0.880	0.910	0.716	142383369



Characteristics

Q3 [%]	x [μm]
10.0	92.5
50.0	163.2
90.0	219.0
SPAN3 = 0.775	
U3 = 1.878	
Mv3(x) = 160.9 μm	
Sigma3(x) = 58.0 μm	

Mean value SPHT3 = 0.893
 Mean value Symm3 = 0.899
 Mean value b/l3 = 0.720
 Mean value RDNS_C3 = 0.587
 Mean value SPHT_K3 = 0.640

User