


B52_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B52_PRECRUSH\B52_PRECRUSH074.rdf
 Task file: C:\CamsizerXT\CAMSYS\B52_PRECRUSH.afg
 Time: 9/16/2015, 15:52, duration 13 min 58 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 1542528, CCD-Z = 29276
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0	0.740	0.865	0.773	5
#30	#20	0.7	100.0	0.764	0.851	0.735	255
#40	#30	3.8	99.3	0.817	0.858	0.744	3878
#50	#40	22.5	95.5	0.884	0.887	0.752	63798
#60	#50	26.2	73.0	0.903	0.899	0.743	141129
#70	#60	22.9	46.8	0.908	0.903	0.729	194505
#140	#70	23.6	23.9	0.896	0.903	0.697	438560
PAN	#140	0.3	0.3	0.836	0.909	0.641	6074771



Characteristics

Q3 [%]	x [μm]
10.0	181.2
50.0	255.2
90.0	365.5
SPAN3 =	0.722
U3 =	1.505
Mv3(x) =	268.1 μm
Sigma3(x) =	84.5 μm

Mean value SPHT3 = 0.886
 Mean value Symm3 = 0.894
 Mean value b/l3 = 0.715
 Mean value RDNS_C3 = 0.516
 Mean value SPHT_K3 = 0.631

User