


B53_01_5KCRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B53_01_5KCRUSH\B53_01_5KCRUSH150.rdf
 Task file: C:\CamsizerXT\CAMSYS\B53_01_5KCRUSH.afg
 Time: 12/21/2015 , 12:33 , duration 34 min 8 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 113245417 , CCD-Z = 1229980
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		1.4	100.0	0.496	0.862	0.664	33
#20	#16	0.5	98.6	0.638	0.848	0.665	78
#30	#20	0.9	98.1	0.683	0.848	0.692	406
#40	#30	1.6	97.2	0.741	0.848	0.711	2048
#50	#40	3.0	95.6	0.777	0.845	0.712	10617
#60	#50	2.9	92.6	0.826	0.856	0.726	21878
#70	#60	6.8	89.7	0.881	0.882	0.748	88908
#140	#70	65.7	82.9	0.903	0.902	0.741	3325057
PAN	#140	17.2	17.2	0.886	0.913	0.726	139455776



Characteristics

Q3 [%]	x [μm]
10.0	79.8
50.0	146.8
90.0	253.0
SPAN3 =	1.179
U3 =	2.023
Mv3(x) =	197.7 μm
Sigma3(x) =	305.4 μm

Mean value SPHT3 = 0.874
 Mean value Symm3 = 0.896
 Mean value b/l3 = 0.720
 Mean value RDNS_C3 = 0.536
 Mean value SPHT_K3 = 0.643

User