


B56_2_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B56_2_PRECRUSH\B56_2_PRECRUSH068.rdf
 Task file: C:\CamsizerXT\CAMSYS\B56_2_PRECRUSH.afg
 Time: 9/14/2015 , 14:34 , duration 12 min 28 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 6696916 , CCD-Z = 121544
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.2	100.0	0.843	0.909	0.770	3
#20	#16	0.3	99.8	0.742	0.884	0.625	10
#30	#20	0.7	99.5	0.800	0.891	0.753	101
#40	#30	2.2	98.8	0.824	0.883	0.756	920
#50	#40	6.2	96.6	0.864	0.886	0.761	7593
#60	#50	8.0	90.4	0.893	0.894	0.760	19494
#70	#60	12.0	82.4	0.908	0.900	0.755	48269
#140	#70	50.1	70.4	0.904	0.904	0.736	733519
PAN	#140	20.3	20.3	0.889	0.926	0.730	19731075



Characteristics

Q3 [%]	x [μm]
10.0	85.2
50.0	168.3
90.0	296.3
SPAN3 = 1.254	
U3 = 2.215	
Mv3(x) = 188.6 μm	
Sigma3(x) = 124.9 μm	

Mean value SPHT3 = 0.890
 Mean value Symm3 = 0.904
 Mean value b/l3 = 0.727
 Mean value RDNS_C3 = 0.617
 Mean value SPHT_K3 = 0.655

User