


B57-1_PRECRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B57-1_PRECRUSH\B57-1_PRECRUSH067.rdf
 Task file: C:\CamsizerXT\CAMSYS\B57-1_PRECRUSH.afg
 Time: 9/15/2015, 8:42, duration 11 min 57 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 2437058, CCD-Z = 42409
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0	0.774	0.938	0.818	1
#20	#16	0.2	100.0	0.756	0.890	0.741	10
#30	#20	0.3	99.8	0.774	0.859	0.740	92
#40	#30	1.4	99.5	0.851	0.880	0.768	1188
#50	#40	12.4	98.1	0.902	0.895	0.769	28287
#60	#50	19.2	85.7	0.917	0.904	0.760	83604
#70	#60	23.3	66.5	0.923	0.908	0.750	160696
#140	#70	41.4	43.2	0.911	0.909	0.720	714229
PAN	#140	1.8	1.8	0.855	0.921	0.683	6085585



Characteristics

Q3 [%]	x [μm]
10.0	152.3
50.0	222.2
90.0	320.3
SPAN3 =	0.756
U3 =	1.565
Mv3(x) =	233.1 μm
Sigma3(x) =	82.5 μm

Mean value SPHT3 = 0.905
 Mean value Symm3 = 0.904
 Mean value b/l3 = 0.726
 Mean value RDNS_C3 = 0.658
 Mean value SPHT_K3 = 0.651

User