


B57_01_6KCRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B57_01_6KCRUSH\B57_01_6KCRUSH093.rdf
 Task file: C:\CamsizerXT\CAMSYS\B57_01_6KCRUSH.afg
 Time: 10/6/2015, 8:21, duration 24 min 4 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 50221516, CCD-Z = 762102
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.805	0.799	0.648	1
#50	#40	0.1	100.0	0.728	0.763	0.730	408
#60	#50	1.9	99.9	0.898	0.884	0.780	24130
#70	#60	19.4	98.0	0.930	0.909	0.778	371418
#140	#70	72.6	78.6	0.920	0.911	0.736	3338521
PAN	#140	6.0	6.0	0.866	0.911	0.695	106788326



Characteristics

Q3 [%]	x [μm]
10.0	123.8
50.0	184.8
90.0	226.9
SPAN3 =	0.558
U3 =	1.567
Mv3(x) =	178.9 μm
Sigma3(x) =	43.3 μm

Mean value SPHT3 = 0.912
 Mean value Symm3 = 0.908
 Mean value b/l3 = 0.727
 Mean value RDNS_C3 = 0.634
 Mean value SPHT_K3 = 0.650

User