


B57_01_7KCRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B57_01_7KCRUSH\B57_01_7KCRUSH097.rdf
 Task file: C:\CamsizerXT\CAMSYS\B57_01_7KCRUSH.afg
 Time: 10/8/2015, 8:29, duration 27 min 20 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 63814515, CCD-Z = 848789
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.528	0.707	0.605	1
#50	#40	0.1	100.0	0.732	0.770	0.739	399
#60	#50	1.8	99.9	0.897	0.884	0.780	21917
#70	#60	18.9	98.1	0.930	0.909	0.778	339514
#140	#70	71.5	79.2	0.919	0.910	0.737	3125927
PAN	#140	7.7	7.7	0.866	0.909	0.697	115592127



Characteristics

Q3 [%]	x [μm]
10.0	117.2
50.0	183.5
90.0	226.4
SPAN3 =	0.595
U3 =	1.647
Mv3(x) =	176.3 μm
Sigma3(x) =	45.9 μm

Mean value SPHT3 = 0.911
 Mean value Symm3 = 0.908
 Mean value b/l3 = 0.727
 Mean value RDNS_C3 = 0.624
 Mean value SPHT_K3 = 0.651

User