


B57_01_8KCRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B57_01_8KCRUSH\B57_01_8KCRUSH129.rdf
 Task file: C:\CamsizerXT\CAMSYS\B57_01_8KCRUSH.afg
 Time: 10/20/2015 , 12:19 , duration 29 min 19 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 62387374 , CCD-Z = 791719
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0	0.979	0.962	0.839	1
#50	#40	0.1	100.0	0.698	0.761	0.720	240
#60	#50	1.6	99.9	0.882	0.876	0.774	9494
#70	#60	16.0	98.3	0.923	0.905	0.777	144854
#140	#70	69.5	82.3	0.916	0.908	0.739	1638881
PAN	#140	12.8	12.8	0.872	0.906	0.704	114894545



Characteristics

Q3 [%]	x [μm]
10.0	90.2
50.0	176.0
90.0	223.8
SPAN3 =	0.759
U3 =	2.073
Mv3(x) =	166.4 μm
Sigma3(x) =	52.7 μm

Mean value SPHT3 = 0.905
 Mean value Symm3 = 0.905
 Mean value b/l3 = 0.726
 Mean value RDNS_C3 = 0.625
 Mean value SPHT_K3 = 0.651

User