


B57_02_PRECRUSH

| | |
|--------------------|--|
| Company: | |
| User: | |
| Result file: | C:\CamsizerXT\CAMDAT\B57_02_PRECRUSH\B57_02_PRECRUSH073.rdf |
| Task file: | C:\CamsizerXT\CAMSYS\B57_02_PRECRUSH.afg |
| Time: | 9/16/2015 , 15:34 , duration 10 min 42 s at 0.5 % covered area, image rate 1:1 , with X-Fall, gap width = 7.0 mm |
| Particle model: | xc_min |
| No. of particles: | CCD-B = 3989274 , CCD-Z = 42747 |
| Velocity adaption: | no |
| Fitting: | no |
| Material: | |

| ASTM(+) | No(-) | retained [%] | passing [%] | SPHT3 | Symm3 | b/l3 | PDN |
|---------|-------|--------------|-------------|-------|-------|-------|---------|
| > #16 | | 0.2 | 100.0 | 0.550 | 0.866 | 0.767 | 3 |
| #20 | #16 | 0.4 | 99.8 | 0.808 | 0.910 | 0.776 | 30 |
| #30 | #20 | 0.8 | 99.4 | 0.796 | 0.889 | 0.752 | 128 |
| #40 | #30 | 0.8 | 98.6 | 0.830 | 0.889 | 0.753 | 360 |
| #50 | #40 | 1.4 | 97.8 | 0.861 | 0.886 | 0.758 | 1984 |
| #60 | #50 | 2.5 | 96.4 | 0.894 | 0.888 | 0.769 | 7625 |
| #70 | #60 | 6.4 | 93.9 | 0.910 | 0.895 | 0.766 | 30731 |
| #140 | #70 | 71.5 | 87.5 | 0.898 | 0.904 | 0.739 | 1419263 |
| PAN | #140 | 16.0 | 16.0 | 0.863 | 0.922 | 0.685 | 9080230 |



| |
|----------------------------|
| Mean value SPHT3 = 0.884 |
| Mean value Symm3 = 0.904 |
| Mean value b/l3 = 0.719 |
| Mean value RDNS_C3 = 0.630 |
| Mean value SPHT_K3 = 0.631 |

User