


B57_3_6KCRUSH

Company:
 User:
 Result file: C:\CamsizerXT\CAMDAT\B57_3_6KCRUSH\B57_3_6KCRUSH077.rdf
 Task file: C:\CamsizerXT\CAMSYS\B57_3_6KCRUSH.afg
 Time: 10/21/2015, 12:18, duration 28 min 47 s at 0.5 % covered area, image rate 1:1, with X-Fall, gap width = 7.0 mm

Particle model: xc_min
 No. of particles: CCD-B = 47631296, CCD-Z = 631655
 Velocity adaption: no
 Fitting: no

Material:

ASTM(+)	No(-)	retained [%]	passing [%]	SPHT3	Symm3	b/l3	PDN
> #16		0.0	100.0				0
#20	#16	0.0	100.0				0
#30	#20	0.0	100.0				0
#40	#30	0.0	100.0				0
#50	#40	0.0	100.0	0.669	0.768	0.689	57
#60	#50	0.5	100.0	0.872	0.870	0.779	3537
#70	#60	5.1	99.5	0.914	0.897	0.779	57403
#140	#70	76.3	94.4	0.912	0.907	0.749	3436911
PAN	#140	18.1	18.1	0.888	0.920	0.712	108326077



Characteristics

Q3 [%]	x [μm]
10.0	91.0
50.0	137.2
90.0	198.8
SPAN3 = 0.786	
U3 = 1.641	
Mv3(x) = 140.9 μm	
Sigma3(x) = 43.8 μm	

Mean value SPHT3 = 0.901
 Mean value Symm3 = 0.907
 Mean value b/l3 = 0.728
 Mean value RDNS_C3 = 0.656
 Mean value SPHT_K3 = 0.653

User